## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1-11 (cancelled).

12 (currently amended). A process for the copolymerisation of ethylene and an  $\alpha$ -olefin having 7 to 10 carbon atoms, comprising the steps of:

providing a fluidised bed gas phase reactor having a reaction zone and a recycle stream;

providing a single site polymerisation catalyst in said gas phase reactor, said catalyst being a metallocene complex represented by the general formula LxMQn wherein L is a cyclopentadienyl ligand, M is titanium, zirconium or hafnium, Q is a leaving group and x and n are dependent on the oxidation state of the metal;

bringing said ethylene and said  $\alpha$ -olefin having 7 to 10 carbon atoms into contact with said single site polymerization catalyst in said reaction zone at a controlled reaction temperature under condensed mode conditions to form a monomer mixture, said condensed mode conditions in the reaction zone being provided by the introduction of said recycle steam comprising a liquid and a gas phase;

maintaining the partial pressure of said alpha  $\underline{\alpha}$ -olefin in the reaction zone below an amount which would, at a temperature of 10 $^{\circ}$ C less than said controlled reaction temperature of said monomer mixture in the reaction zone, be the saturated vapor

pressure of said alpha  $\alpha$ -olefin to thereby prevent condensation of said alpha  $\alpha$ -olefin in

the reaction zone.

13 (previously presented). A process according to claim 12 wherein the partial

pressure of ethylene in the reactor is in the range 0.5 to 2 Mpa.

14 (previously presented). A process according to claim 12 wherein the  $\alpha$ -olefin

is 1-octene.

15 (previously presented). A process according to claim 14 wherein the ratio of

1-octene/ethylene partial pressure is in the range 0.0001 to 0.02.

16 (previously presented). A process according to claim 12 wherein the  $\alpha$ -olefin

is 1-decene.

17 (previously presented). A process according to claim 16 wherein the ratio of

1-decene/ethylene partial pressure is in the range 0.00005 to 0.005.

18 (previously presented). A process according to claim 12 wherein the process

is continuous.

19 (canceled).

20 (currently amended). A process according to claim 12 wherein the metallocene complex has the general formula

wherein:-

R' each occurrence is independently selected from the group consisting of hydrogen, hydrocarbyl, silyl, germyl, halo, cyano, and combinations thereof, said R' having up to 20 non-hydrogen atoms, and optionally, two R' groups (where R' is not hydrogen, halo or cyano) together form a divalent derivative thereof connected to adjacent positions of the cyclopentadienyl ring to form a fused ring structure;

X is hydride or a moiety selected from the group consisting of halo, alkyl, aryl, aryloxy, alkoxy, alkoxyalkyl, amidoalkyl and siloxyalkyl having up to 20 non-hydrogen atoms and neutral Lewis base ligands having up to 20 non-hydrogen atoms,

M is hafnium, titanium or zirconium,

 $Z^*$  is  $SiR^*_2$ ,  $CR^*_2$ ,  $SiR^*_2SIR^*_2$   $SiR^*_2SiR^*_2$ ,  $CR^*_2CR^*_2$ ,  $CR^*_2CR^*_2$ ,  $CR^*_2SIR^*_2$ , or  $GeR^*_2$ , wherein:

R\* each occurrence is independently hydrogen, or a member selected from the group consisting of hydrocarbyl, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said

R\* having up to 10 non-hydrogen atoms, and optionally, two R\* groups from Z\* (when R\* is not hydrogen), or an R\* group from Z\* and an R\* group from Y form a ring system,

and n is 1 or 2 depending on the valence of M.

21 (currently amended). A process according to claim 12 wherein the metallocene complex has the general formula

wherein:-

R' each occurrence is independently selected from the group consisting of hydrogen, hydrocarbyl, silyl, germyl, halo, cyano, and combinations thereof, said R' having up to 20 non-hydrogen atoms, and optionally, two R' groups (where R' is not hydrogen, halo or cyano) together form a divalent derivative thereof connected to adjacent positions of the cyclopentadienyl ring to form a fused ring structure;

X is a neutral  $\eta^4$  bonded diene group having up to 30 non-hydrogen atoms, which forms a  $\pi$ -complex with M:

JACOBSEN et al Appl. No. 10/586,781 August 2, 2011

Y is -O-, -S-, -NR\*-, -PR\*-,

M is titanium or zirconium in the + 2 formal oxidation state;

 $Z^*$  is SiR\*<sub>2</sub>, CR\*<sub>2</sub>, SiR\*<sub>2</sub>SiR\*<sub>2</sub> SiR\*<sub>2</sub>SiR\*<sub>2</sub>, CR\*<sub>2</sub>CR\*<sub>2</sub>, CR\*=CR\*, CR\*<sub>2</sub>SiR\*<sub>2</sub> CR\*<sub>2</sub>SiR\*<sub>2</sub>, or GeR\*<sub>2</sub>, wherein:

R\* each occurrence is independently hydrogen, or a member selected from the group consisting of hydrocarbyl, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said

R\* having up to 10 non-hydrogen atoms, and optionally, two R\* groups from Z\* (when R\* is not hydrogen), or an R\* group from Z\* and an R\* group from Y form a ring system.

22 (previously presented). A process according to claim 20 wherein the metal M is titanium.